



A-36™ Construction grade concrete mix

Repair Thickness

2" – 24"

Set Time

30 minutes

Application Technique

Pour

Where to Use

- Form and pour applications
- Concrete repairs minimum 2" thick
- Partial or full repairs
- Interior or exterior
- High rise buildings
- Balconies, parking garages

Features

- High performance—Technical Grade
- High flow—Long pouring time
- Shrinkage compensated
- Portland cement based
- Includes 3/8" rock
- One component—Just add water
- Freeze thaw durable

Packaging and Yield

65 lb heavy duty polyethylene bag

0.55 cu ft

Product Description

A-36 Concrete Mix is a 1 component, high flow concrete mix. **A-36 Concrete Mix** is mixed with water and applied from 2" thick to full depth. Product includes 3/8" aggregate and flow agents.

A-36 Concrete Mix is a special blend of cement, aggregate and exclusive modifiers. Designed for general purpose and high performance concrete repair or resurfacing applications.

For Best Results

Apply to a clean, dry sound substrate above 40° F. Substrate is to be surface saturated dry (SSD), if applicable, but otherwise hold no standing water prior to application. Check moisture content (mat test) prior to applying any waterproof topping. Do not retemper already mixed material. Do not expose to rain or flowing water during application.

Surface Preparation

Surface preparation is critical to achieve long lasting results. Existing concrete substrate shall be clean, sound, and free of oil, grease, laitance, curing compounds, or any other foreign matter. Saw cut patches at least 1/2" deep and provide a square shoulder. Undercut any exposed rebar 3/4" to provide adequate space for material to encapsulate the reinforcement. Apply JE Tomes approved coating to exposed reinforcement when specified. When applicable, prior to applying **A-36 Concrete Mix**, concrete substrates should be saturated with clean water. Just before applying product, remove any standing water and allow surface to dry. This will leave the substrate saturated surface dry (SSD). A dry substrate may pull moisture from the mixed product during placement and cause cracking or poor bond.

Mixing Guidelines

Force mixing is recommended with a slow speed drill with a Jiffy type paddle or appropriately sized mortar mixer. Approximately 3 qt of water is required to mix 65 lb of product. Always add and mix product into water. When using a hand drill, add dry product slowly while mixing or introduce product in increments and mix in between to reduce lumping and ensure consistency. Vary depth of paddle in mixing container. Mix for 2 to 3 minutes.

Application

Pour into form or apply to a minimum thickness of 2" within 30 minutes.

Curing

Rapid drying of cement-based products may cause cracking or de-bonding. Avoid applications in high winds, excessive heat or blowing air directly on freshly placed product. Curing compounds, wet burlap or polyethylene will reduce rapid drying but may cause color change or mar product surface. If form is used, allow material to cure in form for 2 or more days before removing forms. Allow one day for light traffic on horizontal repairs. Contact JE Tomes if you have any questions or concerns with your application.



Made in the USA by JE Tomes, an American Owned and Operated Company

2513 W. 140th Place • Blue Island, IL 60406

A-36™

Technical Data

Compressive strength, 28 day	Exceeds 5500 psi	ASTM C42
Compressive strength, 7 day	Exceeds 3000 psi	ASTM C42
Compressive strength, 1 day	Exceeds 1500 psi	ASTM C42
Freeze/thaw durability	Excellent	ASTM C666
Air content	6%	
Color	Concrete gray	

LIMITED WARRANTY

JE Tomes & Associates, Inc. warrants its products to be free from manufacturing defects and will deliver, at no charge, an equal amount of packaged product as that amount proven to be defective when applied in accordance with manufacturer's written directions by contractors experienced in this application, and used in applications recommended by the manufacturer as suitable for the product. All claims concerning product defects must be made within twelve (12) months of use of the product. THERE ARE NO OTHER WARRANTIES BY JE TOMES & ASSOCIATES, INC. OF ANY NATURE WHATSOEVER, EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH PRODUCTS WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. Buyer's sole and exclusive remedy for breach of any warranty shall be replacement of defective product. JE Tomes & Associates, Inc. shall not be liable for any damages, including consequential damages, except as otherwise set forth therein.