

10 Minute JET-Crete

JET-25: 2 Cartridge Starter Kit

www.jetomes.com


Description: Contains 2 cartridges of 10 Minute Concrete Mender, a high-penetration, two-part, cross-link urethane that combines with sand to form a tough instant polymer concrete that cures in approximately 10 minutes from application at 70° F. (21°C)

Features: Extremely low viscosity for deep penetration. Cures in a wide climate range from 100° F down to subzero temperatures. High chemical resistance. Safe to use with very little odor. Cartridge is completely self-mixing.

Benefits: Long lasting repairs that won't get brittle and pop out. Easy preparation. No downtime, repairs may be opened to traffic 10 minutes after application at 70° F.

Limitations: Recommended for non-movement repairs. For moving repairs use our Flexible Cement. Not color-fast when exposed to UV light. Repairs in areas exposed to sunlight should be painted, coated or resurfaced. **For Professional use only. Read MSDS and product data sheets prior to use.**

For product shipping emergency involving a spill, leak, exposure or fire, contact Chem-Tel: 800-255-3924

LIMITED WARRANTY

JE Tomes & Associates, Inc. warrants its products to be free from manufacturing defects, and will deliver, at no charge, an equal amount of packaged product as that amount proven to be defective when applied in accordance with manufacturer's written directions by contractors experienced in this application, and used in applications recommended by the manufacturer as suitable for the product. All claims concerning product defects must be made within twelve (12) months of use of the product. THERE ARE NO OTHER WARRANTIES BY JE TOMES & ASSOCIATES, INC. OF ANY NATURE WHATSOEVER, EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH PRODUCTS WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. Buyer's sole and exclusive remedy for breach of any warranty shall be replacement of defective product. JE Tomes & Associates, Inc. shall not be liable for any damages, including consequential damages, except as otherwise set forth therein.

Uses: Repairing cracks, spalls, and holes in concrete surfaces. Anchoring bolts and railings plus dozens of other uses.

Surface Preparation and Application: Remove loose dirt, dust, and concrete with a wire brush or diamond blade grinder. See application instructions enclosed.

Packaging & Yield

Contents:

- 2 300x300 ml Cartridges of 10 Minute Concrete Mender
- 1 300x300 ml Cartridge Application Tool
- 10 lbs of 10 Minute Concrete Mender Sand
- 3 lbs of Dry Latex Concrete Resurfacer
- 1 Plastic Margin Trowel
- 1 Pair of Disposable Gloves
- 1 packet with instructions, data and MSDS information

Yield: Approximately 200 linear feet at 1/4" wide by 1/4" deep or 244 cubic inches when mixed 2 parts sand to 1 part liquid.

KEEP CARTRIDGES IN A COOL, DRY PLACE. STORE AT ROOM TEMPERATURE BETWEEN 50-80° F

WARNING: CONTAINS (MDI) ISOCYANATE. MAY BE SKIN AND RESPIRATORY SENSITIZER. MAY CAUSE IRRITATION, OF EYES, SKIN, NOSE, AND THROAT. Do not breathe vapors. Use with adequate ventilation. Avoid contact with eyes, skin and clothing. **Wear safety glasses and protective gloves.** FIRST AID: In all cases seek appropriate medical attention immediately. INHALATION: Move to fresh air. INGESTION: Do not induce vomiting. Drink water. EYES: Flush open eyes with water for 15 minutes. SKIN: Wash with soap and water.

WARNING: Contains cement and silica, avoid inhalation of dust. Wear gloves, safety goggles and OSHA approved dust respirator during mixing and placement. Refer to product MSDS (Material Safety Data Sheet) for additional safety information. Do not take internally. Avoid prolonged contact with skin. FOR INDUSTRIAL USE ONLY. KEEP OUT OF THE REACH OF CHILDREN.

Technical Information

Cure time @ 72° F (22° C)	10 min
Gel time @ 72° F (22° C)	6-7 min
Compressive Strength (with sand)	4500 psi
Hardness @ 72° F (22° C)	72D
Elongation	6%
Tensile Strength	4475 psi
Bond Strength (ASTM 882-99)	1984 psi
Viscosity (at application)	<9 cps
Surface Tension (Wilhelmy Plate)	0.026 N/m
V.O.C. (mixed)	5.5 g/l
Solids	98%
Mixing Ratio	1:01
Cured Color	Gray